

## MACal® 9722-00 PRO Light Stop

### PRODUCT DESCRIPTION

MACal 9722-00 PRO is a vinyl 100 % opaque coated with a long-life durable, highly cohesive acrylic pressure sensitive adhesive, which is protected with a high quality siliconized kraft paper.

#### Face material:

Totally opaque white film, 140 µm thick, cadmium-free, with a matt finish which prevents light reflection.

#### Adhesive:

Acrylic based pressure-sensitive, very cohesive and extremely durable.

#### Liner:

Highly stable 135 gsm bleached kraft paper printed with MACal 9700 PRO logo in blue.

### TYPICAL USE

MACal 9722-00 PRO Light Stop can be used for light box applications (in combination with MACal 9700 PRO colours and MACal 9700 PRO Light Diffusers). This film stops the light going through and allows special effects when the light box is lit.

### PROCESSING

Computer cutting

Clean, efficient, trouble-free cutting with most plotters. Adjustment of the depth of the cutting tool is important, as too deep a cut into the liner could result in the paper splitting when transferred onto the Application Tape.

### SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

### APPLICATION METHOD

The transfer of the cut vinyl onto the application tape should always be performed by removing the liner from the pressure-sensitive material (i.e. with the PVC face downwards onto the working surface) and not by lifting off the application aape.

### IMPORTANT REMARK

All surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination. The compatibility of paints and lacquers should be tested by the end-user, prior to use.

Care should be taken when selecting a substrate for use in illuminated devices with self-adhesive materials. Some substrates, e.g. polycarbonate could degas and create 'bubbling' defects.

It is, therefore, recommended to conduct compatibility trials between MACal 9722-00 PRO

Light Stop and the application surface before making large jobs.

### PHYSICAL PROPERTIES (TYPICAL VALUES)

Face Material Data, 23°C	Average values	Test method
Tensile strength (kN/15mm)	>1.1	DIN ISO 527-3
Elongation at break (%)	>100	

#### Thickness

Face film + adhesive (µm)	175	ISO 534
---------------------------	-----	---------

#### Adhesive data, 23°C (N/25 mm)

Peel on mirror Stainless Steel		FTM 1
20 minutes	14	
24 hours	20	
1 week	24	

#### Dimensional stability

Shrinkage (1 week at 70°C applied on aluminium)	Max. 0.7 mm	FTM 14
--	-------------	--------

#### Flammability

Sample mounted on aluminium	self-extinguishing	ISO 3795
-----------------------------	--------------------	----------

#### Temperature ranges

Minimum application temperature	10°C
Service temperature range of use	- 40°C to + 90°C

### EXPECTED DURABILITY

Central Europe Zone 1

Unprocessed	7 years	ISO 4892-2
-------------	---------	------------

Note : Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitudes and south-facing exposure. No durability warranty is given for horizontal exposure.

Important notice Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

Disclaimer and warranty Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.