

**GRAPHICS** - Overlaminating FilmsIssue date : 05/01/2005  
Date last modification : 30/10/2019**4-GL2B-03097 RI-6480 ANTIGRAFFITI UV SCREEN PROTECTED CLEAR AP906 PERMANENT PET30****Face Material**

Gloss clear polyester.

Type	LH polyester	
Colour and Finish	Gloss clear	
Weight	28 g/m <sup>2</sup> ±10%	ISO-536
Thickness	20 µ ±10%	ISO 534-80

**Adhesive**

Solvent based permanent acrylic adhesive featuring good water and cleaning agents resistance. High adhesion on a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

Reference	AP906 permanent	
Type	Acrylic permanent	
Min. Appl. Temp.	+10°C	
Service Temp.	-20°C/+140°C	
Shear	Very high	
Tack	High N/inch <sup>2</sup>	
Final Adhesion	Very high N/inch	

**Liner**

Type	One side siliconised polyester	
Colour and Finish	Clear	
Weight	42 g/m <sup>2</sup> ±10%	PP-032 - ISO 536
Thickness	30 µ ±10%	ISO 534
Transparency	>95 %	DIN 53 147-64

**Applications**

Offers extreme high clarity, very high UV resistance and also has excellent anti-graffiti properties.

- Outdoor vertical exposure durability: UP TO 3 YEARS.  
The Durability data are given for unprinted films only and based on Zone 1 exposure conditions (Northern and Eastern Europe, Italy, France).

**Printing Methods**

Not printable.

Testing for suitability between media, printers and inks is always recommended prior to use.

**Shelf life**

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.